



**JLB002 WATERBORNE
ACRYLIC TOPCOAT
Technical Data Sheet**

Properties and uses:

The waterborne acrylic topcoat consisting of waterborne acrylic resin, pigments, auxiliary agent, drier and deionized water.

- It utilize water as the dispersion medium, ,non-flammable, non-explosive, and zero-pollution.
- It is safe and convenient to use, non-toxic to human body.
- Good workability
- Good weather resistance and decorative properties.

It is suitable for decoration and protection of various steel structures, vehicles, agricultural machinery, industrial equipment, vessels, etc.

Physical Parameters:

Color:	White & a range of colors
Sheen:	Matte
Standard film thickness:	Wet film: 90μm
Dry film:	30μm
Theoretical Coverage:	11.1m ² /L
Specific Gravity	Approx.1.25

Application Note:

Mix Ratio:	Single Component, it can be used directly		
Thinner:	De-ionized water		
Application Method:	Airless Spray	Air Spray	Brush/Roller
Tip Range: (Graco)	163T-619/621	2-3mm	
Spray Pressure (Mpa):	12-15	0.3-0.4	
Thinning (by Volume):	0-5%	0-15%	0-5%
Tool's Cleaner: Tap Water			

Drying Time:

Substrate Temperature (°C)	Touch Dry (h)	Hard Dry (h)	Recoat Interval (h)	
			Min.	Max.
5	6	12	48	No limit
20	1.5	6	12	..
30	1	4	4	..

SURFACE PREPARATIONS:

The surface of the substrate coated with inter-primer or primer must be clean and dry, and dirt adhered to the surface shall be removed with

appropriate detergent and high-pressure fresh water.

Application Conditions:

Coating shall be made at a temperature range of 5-30℃ with a relative humidity below 95%, the surface temperature of the substrate shall be 3℃ above the dew point, and the temperature and humidity should be measured near the substrate. It is recommended not to carry out coating construction when substrate's surface temperature is over 40 ℃. Coating may not be made in severe weather such as rain, snow, sandstorm, etc.,

Relevant Products:

Waterborne Acrylic Primer
Waterborne Epoxy Resin Primer
Waterborne epoxy primer
HJ120 Modified Epoxy General Primer

Package & Specification:

20L or 10L

Storage: This product shall be stored in a cool, dry and ventilated indoor warehouse with a storage period of one year in ambient temperature.

Safety Any fire source is extremely prohibited near paint preparation spot and application site, proper ventilation is required for mixing and application relevant to this product. Painters have to equip themselves with protective measures so as to prevent the eyes, skins, etc., from injured by the paint mist. If the paint splashes on the skin, it should be washed with soap and water immediately, and then seek medical attention.

Statement

1. The protective effect of any coating depends to a large extent on the coating work, the coating's service life is directly affected by the surface treatment, thickness of paint film and other painting factors, therefore, the users should meet the agreed Application Conditions when using this product.
2. The data shown in this manual are theoretical values or the one accumulated through experiments and some data may be changed without prior notice along with the product's continuous improvement.
3. The company is only responsible for the quality of the coating product itself when the company's technicians are not at the coating site.